In the Claims:

Please amond the claims as set forth below:

Claims 1-12 (Canceled)

13. (Currently Amended) A method of forming a structural assembly, comprising the step of: affixing a first pre-cured assembly to a 3-D woven textile pre-form impregnated with an uncured resin, an adhesive film being located between said first pre-cured assembly and said pre-form, said pre-form having a base and two legs extending from the base, said first pre-cured assembly being located on a side of the base opposite the legs;

affixing at least one additional a second pre-cured assembly to between said legs of said 3-D woven textile pre-form with an additional adhesive film being located between said at least one additional second pre-cured assembly and inner surfaces of said legs of said pre-form; and

curing said resin and said adhesive films to form the structural assembly:; wherein said curing is performed by placing a leg side of a first pressure intensifier of flexible material against an exterior surface of one of said legs and placing a base side of said first pressure intensifier against said base, and placing a leg side of a second pressure intensifier of flexible material against an exterior surface of the other of said legs and placing a base side of said second pressure intensifier against said base, each of said pressure intensifiers having an exterior side that extends from an edge of said base side to an edge of said leg side; and

inserting said first and second pre-cured assemblies along with said pre-form, adhesive films, and pressure intensifiers into a vacuum bag, then evacuating the vacuum bag, causing the pressure intensifiers to press said base and legs of said pre-form against portions of said pre-cured assemblies.

14. (Currently Amended) The method of Claim 13, wherein said 3-D woven textile pre-form is impregnated with an uncured resin said base side and said leg side of each of said pressure intensifiers are at right angles to each other, and each of said pressure intensifiers is triangular in cross section.

D4

- 15. (Currently Amended) The method of claim 13, wherein said first pre-cured assembly and said at least one additional second pre-cured assembly are pre-cured, laminated composite structures.
- 16. (Previously Amended) The method of Claim 13, wherein said step of curing is implemented with heat and pressure.
- 17. (Currently Amended) The method of claim 13, wherein said perform has an exterior portion that is not located between said pre-cured assemblies, and pressure is applied with a pressure intensifier located in contact with said exterior surface of said 3-D woven textile pre-form, the pressure intensifier pressing said exterior portion against a portion of one of said pre-cured assemblies base side and said leg side of each of said pressure intensifiers are equal in length.

D4

- 18. (Currently Amended) The method of claim 13, wherein said step of curing is implemented by inserting said first and second pre-cured assemblies along with said pre-form and adhesive films into a vacuum bag, then evacuating the vacuum bag and heating the vacuum bag said exterior side of each of said pressure intensifiers is concave.
- 19. (Currently Amended) The method of claim 16 13, wherein said step of curing is implemented with an E-Beam resin system.
- 20. (Currently Amended) The method of claim 16_13, wherein said pre-form has at least one exterior portion that is not located between said pre-cured assemblies, the method further comprising the step of applying a composite overwrap ply on said exterior portion_surfaces of said 3-D woven textile pre-form legs of said pre-form prior to pressing said leg sides of said pressure intensifiers against said legs.

21. (Canceled)

- 22. (Currently Amended) The method of claim 21_13, wherein said flexible material pressure intensifiers are is rubber.
- 23. (Currently Amended) The method of claim 13, wherein said 3 D woven textile pre-form further comprises a base and a leg extending from said base at an angle relative to said base a line extending normal to said exterior side of each of said pressure intensifiers passes through a corner formed by a junction of said base with one of said legs.
- 24. (Currently Amended) A method of forming structural assemblies with pre-cured laminated composite structures, comprising the steps of:

providing a woven textile pre-form with a base and at least one leg a pair of legs extending from the base at an a 90 degree angle, the pre-form being impregnated with an uncured resin;

affixing a first adhesive film between a first pre-cured laminated composite structure and the base of the pre-form;

affixing an additional adhesive film between <u>one side of at least one additional a second</u> pre-cured laminated composite structure and <u>an inner surface of one of the leg legs</u> of said 3-D woven textile pre-form, and inserting an additional adhesive film between an opposite side of <u>said second pre-cured laminated composite structure and an inner surface of the other of said legs</u>; then

providing a pair of flexible pressure intensifiers, each being triangular in cross section, and placing one of said pressure intensifiers in contact with said base and an exterior surface of one of said legs and the other of said pressure intensifiers in contact with said base and an exterior surface of the other of said legs; then

enclosing said first and second pre-cured laminated composite structures, said pre-form and said pressure intensifiers within a vacuum bag and evacuating the bag; then

curing said adhesive films and said 3-D woven textile pre-form to form the structural assemblies.

25. (Currently Amended) The method of claim 24, wherein said 3-D woven textile pre-form is impregnated with an uncured resin_each of said pressure intensifiers has a base side that contacts

D4

Houston\1563154.1 6

said base of said pre-form, a leg side that contacts said exterior surface of one of said legs of said pre-form and a concave exterior side that extends from an edge of said base side to an edge of said leg side.

26. (Currently Amended) The method of claim 24, wherein the leg of said pre form is not located between the composite structures, and pressure is applied during said curing step with a flexible pressure intensifier located in contact with an exterior surface of said leg of said 3 D woven textile pre form to force said leg against one of said composite structures each of said pressure intensifiers has a base side that contacts said base of said pre-form, a leg side that contacts said exterior surface of one of said legs of said pre-form, and an exterior side that extends from an edge of said base side to an edge of said leg side; and wherein

a line normal to said exterior side bisects a corner defined by an intersection of said base of said pre-form and one of said legs,



- 27. (Currently Amended) The method of claim 24, wherein said step of curing is implemented by inserting said first and second pre-cured assemblies along with said pre-form and adhesive films into a vacuum bag, then evacuating and heating the vacuum bag.
- 28. (Currently Amended) The method of claim 26_24, wherein said step of curing is implemented with an E-Beam cure resin system.
- 29. (Currently Amended) The method of Claim 27 24, further comprising the step of applying a composite overwrap ply on said exterior surface surfaces of said 3 D woven textile legs of said pre-form
- 30. (Canceled)
- 31. (Canceled)
- 32. (Currently Amended) The method of Claim 24, wherein said 3-D-woven textile pre-form further comprises at least one fiber woven through an intersection of said base and said leg .each

Houston\\\ 563154.1

of said pressure intensifiers has a base side that contacts said base of said pre-form, a leg side that contacts said exterior surface of one of said legs of said pre-form, and an exterior side that extends from an edge of said base side to an edge of said leg side; and wherein.

said base side and said leg side of each of said pressure intensifiers are of the same length.

- 33. (Canceled)
- 34. (Canceled)
- 35. (Canceled)
- 36. (Canceled)
- 37. (Canceled)
- 38. (Canceled)

39. (Currently Amended) The method of Claim 13 24, wherein said 3-D woven textile pre-form is Pi-shaped legs and said base of said pre-form have tapered edges.

- 40. (Canceled)
- 41. (Canceled)
- 42. (Canceled)
- 43. (Currently Amended) The method of Claim 24, wherein said 3-D woven textile pre form has an additional leg extending from the base, defining a pi-shape wherein said pressure intensifiers are formed of rubber.



44. (Canceled)

45. (Currently Amended) The method of Claim 13, wherein said pre-form has at least one exterior surface that is not located between the pre-cured assemblies, the method further comprising tapering a thickness of the pre-form at an edge of said exterior surface of the pre-form tapered edges.

46. (Currently Amended) A method of forming structural assemblies with pre-cured laminated composite structures, comprising the steps of:

providing a woven textile pre-form with a base and a pair of legs extending from the base at an angle, defining a slot between them and corners at intersections of the legs and the base, the pre-form being impregnated with an uncured resin;

affixing a first adhesive film between a pre-cured laminated composite first structure and the base of the pre-form on a side opposite the legs;

inserting a pre-cured laminated composite second structure into the slot with additional adhesive films between inside surfaces of the legs and the second structure;

providing a pair of flexible pressure intensifiers, each of the pressure intensifiers being a three-sided polygon in cross-section, having two straight inner sides intersecting each other, defining a corner portion and an exterior side that extends between edges of the inner sides, and placing the corner portion of each in contact with one of the corners formed by the base and the legs; then

inserting the first and second structures, along with the pre-form, adhesive films and pressure intensifiers into a vacuum bag; and

evacuating the vacuum bag and applying heat to cure said adhesive films and pre-form to form the structural assemblies.

